



ELASTO-SEAL/BOND-KOTE™ 260

**Ultra-Premium Ultra-Low VOC
Elastomeric Sealer Bonder
SBE260**



PRODUCT INFORMATION: ELASTO-SEAL/BOND-KOTE™ 260 - Primer is an advanced technology exterior ultra-low VOC acrylic elastomeric sealer bonder formulated for porous, soft, weathered surfaces, This product neutralizes pH factors, hot spots, and retards efflorescence buildup. Is ideal for use on, commercial, residential, and industrial projects where weatherproof, elastomeric, penetrating sealer bonder is required on stucco, masonry, wood products. Ultra-premium ingredients provide supreme performance, resilience, and adhesion.

PRODUCT DATA SHEET

PRODUCT TYPE: Waterborne
RESIN TYPE: Elastomeric 100% acrylic.
STOCK COLORS : Transparent.
TINT BASES : Transparent.
VISCOSITY @77°F/25°C (ASTM D 562): 92–100 KU
MAXIMUM VOC CONTENT 45 g/L (as supplied)
SOLIDS BY VOLUME 50.0% ± 2%
SOLIDS BY WEIGHT 50.0% ± 2%
WEIGHT PER GALLON (ASTM D 1475): 8 lbs.
RECOMMENDED FILM THICKNESS PER COAT Wet: 4.5 mils Dry: 1.9 mils
AVERAGE DRY TIME @77°F/25°C (ASTM D 1640) To touch: 30 minutes Recoat: After 4-6 hours Dry times and recoat times are temperature, humidity and film thickness dependent.
APPROXIMATE COVERAGE AT RECOMMENDED DRY FILM THICKNESS PER COAT Approximately 200-250 sq. ft. per gallon, depending on surface conditions and application techniques.
PRODUCT PACKAGING: Five-gallon pails
DILUTING RECOMMENDATION: This paint is intended to be applied at package consistency under normal environmental and application conditions.
SURFACE PREPARATION: Remove peeling, loose, or chalky coating by scraping, sanding, sandblasting, or other suitable methods. Repair all holes, cracks, and other surface imperfections with an appropriate repairing material. Repaired surfaces should be sanded and brushed clean. Glossy surfaces should be dulled to provide a profiled surface for proper adhesion. Surfaces must be clean, cured, dry, and free of, mildew, efflorescence, dust, rust, stains, oil, grease, wax, bond-breakers, and any other contaminants that could adversely affect adhesion..
APPLICATION EQUIPMENT: Spray, brush, roller.
PRODUCT CLEANUP: Clean tools with water. Do not allow spills to dry. Clean-up immediately with warm soapy water.
PRODUCT STORAGE: Store in a dry area off the ground. Protect from freezing. Protect from temperatures above 100°F for extended periods of time. Caution, extreme temperatures may cause paint to become unusable.
LEFTOVER PRODUCT DISPOSAL For information on local options to dispose of unwanted leftover product visit https://search.earth911.com/?what=Paint .

CONFORMS TO:
NOTICES / DIRECTIVES
<ul style="list-style-type: none"> NOTICE: Scraping or sanding surfaces of older buildings (especially pre-1978) may release dust containing lead or asbestos. EXPOSURE TO LEAD OR ASBESTOS CAN BE VERY HAZARDOUS TO YOUR HEALTH. Always wear appropriate personal protective equipment during surface preparation, and finish cleanup of any residues by water-washing all surfaces. For more information about the health effect of exposure, call EPA's National Lead and Asbestos Information Hotline at 1-800-424-LEAD, or visit www.epa.gov/lead or www.epa.gov/asbestos. NOTICE: Safety Data Sheets available at https://shanecoatings.com NOTICE: For information on local options to dispose of unwanted leftover paint visit https://search.earth911.com/?what=Paint. NOTICE: Excessive moisture and inadequate ventilation are the main conditions that promote the growth of mold and mildew. Correct these conditions before painting. This product cannot prevent, cause, or cure the growth of mold, mildew, or any form of fungus. DIRECTIVE: Do not mix with other products. DIRECTIVE: Do not apply when the air or surface temperature is below 40°F.

APPLICATION

TEMPERATURE: 50°F minimum, 90°F maximum (air, surface and material). Surface temperature must be at least 5°F above dew point.

RELATIVE HUMIDITY: 90% maximum

	SPRAY	BRUSH	ROLLER
PRESSURE: 2000-2500 psi		Polyester/Nylon	3/8" nap
TIP SIZE: 0.13 - 0.15			

DISCLAIMER: The information contained in this Product Data Sheet publication are based upon field data conducted by or on behalf of SCMFG Corporation. Such information and recommendations set forth herein can advance and change over time and pertain to the product offered at the time of publication. Consult your Sales representative to obtain the most recent Product Data Information and Application Procedures.